



# TECHNICAL DATA SHEET



**Noelle Industries, Inc.**  
Adhesives • Coatings • Conductives • Encapsulants

## NOELLE 805-16

### A Two Component Quickset Epoxy Adhesive

#### **Description:**

Noelle 805-16 System is a clear two component (A + B) high performance, room temperature curing, quickset epoxy Adhesive.

#### **Advantages:**

Noelle 805-16 will cure at temperatures above 15°C (60°F) in a short period of time.

#### **Physical Properties:**

	<b><u>Resin</u></b>	<b><u>Hardener</u></b>
	805-16A	805-16B
Color:	Clear	Clear
Specific Gravity	1.16	0.98
Mix Ratio		
(By Volume)	1.0	1.0
(By Weight)	100	100

#### **Shelf Life:** (Sealed containers)

One Year @ 25°C (both A+B). Hand agitation of the Resin component is recommended after long standing to insure best results.

#### **Instructions:**

Combine the Resin and the Hardener in the ratio listed above. Mix by hand or mechanical mixer until material is uniform in appearance.

#### **Cure Schedules:**

2 hours @ 25°C (77°F) will yield 80% of the systems full potential. An additional 22 hours @ 25°C (77°F) will yield the systems full potential.

	80%	100%
Cure Temp:	25°C	25°C
Cure Time:	2 hrs	24 hrs

**Pot Life**( 6 grams) @ 25°C = 3.5 to 5.5 min

#### **Cured Properties:**

Shore Hardness, measured @ 25°C 84D  
Operating Temperature Range: -20°C to +100°C

#### **Storage and Handling:**

Normal storage and handling is at room temperature. Use standard mixing and house keeping procedures to minimize the risk of spills and contact with the surrounding materials.

All values reported above are typical values, and are reported as a means of reference. Individual testing should be done to determine actual results, tested at specific conditions.

• 76 Treble Cove Road, Building # 3, Unit C, North Billerica, MA 01862

• Phone: (978) 439-9841 • Fax: (978) 439-9842 • Website: [www.noelleindustries.com](http://www.noelleindustries.com) • email: [info@noelleindustries.com](mailto:info@noelleindustries.com)