



Noelle Industries, Inc.

Adhesives • Coatings • Conductives • Encapsulants

76 Treble Cove Road, Unit C - N. Billerica, MA 01862

United States of America

Phone: (978) 439-9841 - Fax: (978) 439-9842

Website: www.noelleindustries.com

Email: info@noelleindustries.com



QUALITY SYSTEM
REGISTERED TO
ISO 9001:2000

TECHNICAL DATA SHEET NOELLE 805-94

A Two Component Epoxy Adhesive

Description:

Noelle 805-94 System is a two component (A + B) medium viscosity, unfilled epoxy system designed for adhesive and coating applications, that either meets or exceeds the requirements for FDA approval to CFR21 chapter 1, Sections 175.105 and 175.300 and has been tested and certified to meet USP Class VI requirements.

Advantages and Applications:

Noelle 805-94 features a moderate cure time and a convenient mix ratio. Noelle 805-94 is a durable adhesive that bonds to a variety of substrates and dissimilar materials. Noelle 805-94 System is 100% solids and undiluted which yields very low vapor transmission. Applications include medical devices, general purpose metal to metal bonding. Noelle 805-94 is resistant to galvanic corrosion, fuels, and mild acids.

Physical Properties:

	Resin	Hardener
	805-94A	805-94B
Color:	Clear	Amber
Specific Gravity	1.16	0.98
Combined	1.07	
Viscosity	14,000 cps.	14,000 cps.
Mix Ratio		
(By Volume)	1.0	0.85
(By Weight)	100.0	100.0

(May also be used at 1 to 1 by weight)

Shelf Life: (Sealed containers) One Year @ 25°C (both A+B). Hand agitation of the Resin component is recommended after long standing to insure best results.

Instructions:

Combine the Resin and the Hardener in the ratio listed above. Mix by hand or mechanical mixer until material is uniform in appearance and color (Lt Amber).

Cure Schedules:

(Within an 10 hour period after application @ 25°C will yield 80% of the systems full potential. An additional 6 hours @ 25°C will yield the systems full potential. Post curing or forced air curing for 2 hours at 65°C will yield a full cure and eliminate the additional waiting time at ambient temperature).

	80%	100%	or	100%
Cure Temp:	25°C	25°C		65°C
Cure Time:	10 hrs	16 hrs		2 hrs
Pot Life (450 grams) @ 25°C	90 min			

Cured Properties:

Shore Hardness, measured @ 25°C	>70D
Dielectric Strength, Volts per mil	440
Lap Shear, Tensile Strength Al/Al ASTM D-1002:	
	34 M Pa
Compressive Strength:	66 M Pa
Flexural Strength:	54 M Pa
Coefficient of Linear Thermal Expansion (cm/cm/°C):	
	60 x 10 ⁻⁶
Operating Temperature Range:	0°C to +100°C
Cured Shrinkage:	0.001 in/in

Storage and Handling:

Normal storage and handling is at room temperature. Use standard mixing and house keeping procedures to minimize the risk of spills and contact with the surrounding materials.

All values reported above are typical values, and are reported as a means of reference. Individual testing should be done to determine actual results, tested at specific conditions.