



# TECHNICAL DATA SHEET



Registered to  
ISO 9001

## Noelle Industries, Inc.

Adhesives • Coatings • Conductives • Encapsulants

### NOELLE 807-38

#### A Two Component Epoxy Potting and Coating Compound.

#### Description:

Noelle 807-38 System is a two component (A + B) unfilled, heat curing, liquid epoxy encapsulant and potting and coating compound.

#### Advantages and Applications:

Noelle 807-38 is designed as an impregnating liquid epoxy for filament windings, small device potting and area's that require a low viscosity or low surface area material. Noelle 807-38 is used as a low viscosity mixture that exhibits exceptional wetting and void free pourings during application.

#### Physical Properties:

	<u>Resin</u>	<u>Hardener</u>
	807-38A	807-38B
Color:	Clear	Brown
Specific Gravity	1.14	1.11
Combined	1.14	
Mix Ratio		
(By Volume)	3.50	1.00
(By Weight)	100	28

#### Shelf Life: (Sealed containers)

One Year @ 25°C (both A+B). Hand agitation of the Resin component is recommended after long standing to insure best results.

#### Instructions and Surface Preparation:

Combine the Resin and the Hardener in the ratio listed above. Mix by hand or mechanical mixer until material is uniform in appearance and color (Brown). For best results the unit to be potted should be free of grease or contamination before potting

#### Cure Schedules:

Cure Temp:	80°C	90°C	110°C
Cure Time:	4 hrs	3 hrs	2 hrs

**Pot Life** (100 grams) @ 25°C = >4 Hour

#### Cured Properties:

Shore Hardness, measured @ 25°C	>80D
Volume Resistivity, Ohm/cm @ 25°C:	3 x 10 <sup>14</sup>
Coefficient of Linear Thermal Expansion (in/in°C):	4.4 x 10 <sup>-5</sup>
Dielectric Constant @ 1 MHz @ 25°C:	3.8
Dissipation Factor @ 1 MHz @ 25°C:	0.024
Glass Transition Temperature (t <sub>g</sub> ):	>110°C

#### Storage and Handling:

Normal storage and handling is at room temperature. Use standard mixing and housekeeping procedures to minimize the risk of spills and contact with the surrounding materials. If hardener crystallizes, heat to 60°C to return to liquid form.

All values reported above are typical values, and are reported as a means of reference. Individual testing should be done to determine actual results, tested at specific conditions.

• 76 Treble Cove Road, Building # 3, Unit C, North Billerica, MA 01862

• Phone: (978) 439-9841 • Fax: (978) 439-9842 • Website: [www.noelleindustries.com](http://www.noelleindustries.com) • email: [info@noelleindustries.com](mailto:info@noelleindustries.com)