



TECHNICAL DATA SHEET

Noelle Industries, Inc.
Adhesives • Coatings • Conductives • Encapsulants

NOELLE 807-45

A Two Component Epoxy Paste Adhesive

Description:

Noelle 807-45 System is a two component (A + B) mineral filled, room temperature fast curing, paste epoxy adhesive

Advantages and Applications:

Noelle 807-45 features exceptional adhesion, strength and durability, along with ease of application. Noelle 807-45 is formulated for fast set up and is capable of curing in the vertical position. Noelle 807-45 has good chemical resistance.

Physical Properties:

	<u>Resin</u>	<u>Hardener</u>
	807-45A	807-45B
Color:	Light Gray	Tan
Specific Gravity:	1.51	1.54
Combined:	1.53	
Mix Ratio		
(By Volume):	2.00	1.00
(By Weight):	2.00	1.00

Shelf Life: (Sealed containers)

One Year @ 25°C (both A+B). Hand agitation of the Resin component is recommended after long standing to insure best results.

Instructions and Surface Preparation:

Combine the Resin and the Hardener in the ratio listed above. Mix by hand or mechanical mixer until material is uniform in appearance and color (Light Gray). To insure best results the surface should be sand or grit blasted. A grinding wheel or stiff wire brush can be used on the surface and followed with a solvent wipe.

Cure Schedules:

Within a 16 hour period after application @ 25°C will yield 80% of the systems full potential. An additional 8 hours @ 25°C will yield the systems full potential. Post curing or forced air curing for 2 hours at 65°C will yield a full cure and eliminate the additional waiting time at ambient temperature.

% Full Cure:	80%	100% or	100%
Cure Temperature:	25°C	25°C	65°C
Cure Time (hours):	16	24	2

Pot Life (50 grams) @ 25°C 20 minutes

Cured Properties:

Shore Hardness, measured @ 25°C:	>78D
Lap Shear, Tensile Strength, Al/Al ASTM D-1002 (psi):	>3000
Compressive Strength, (psi):	>8100
Flexural Strength, (psi):	>6200
Coefficient of Linear Thermal Expansion, (in/in °C):	35 x 10 ⁻⁶
Cured Shrinkage, (in/in):	0.05
Operating Temperature Range, (°C):	0°C to +100°C

Storage and Handling:

Normal storage and handling is at room temperature. Use standard mixing and housekeeping procedures to minimize the risk of spills and contact with the surrounding materials.

All values reported above are typical values, and are reported as a means of reference. Individual testing should be done to determine actual results, tested at specific conditions.

• 76 Treble Cove Road, Building # 3, Unit C, North Billerica, MA 01862

• Phone: (978) 439-9841 • Fax: (978) 439-9842 • Website: www.noelleindustries.com • email: info@noelleindustries.com