



**Noelle Industries, Inc.**  
*Adhesives • Coatings • Conductives • Encapsulants*



76 Treble Cove Road, Unit C - N. Billerica, MA 01862  
 United States of America  
 Phone: (978) 439-9841 - Fax: (978) 439-9842  
**Website: [www.noelleindustries.com](http://www.noelleindustries.com)**  
 Email: [info@noelleindustries.com](mailto:info@noelleindustries.com)

## TECHNICAL DATA SHEET

### NOELLE 808-72 System

#### A Two Component Transparent Silicone Dielectric Gel

#### **Description:**

Noelle 808-72 System is a soft, transparent, two component (A + B) high performance, thickened, fast room temperature curing, silicone dielectric gel adhesive. Noelle 808-72 System is designed for use in applications that requires a flexible, shock resistant, and cushion coat material for sensitive or fragile components or fine electrical wires.

#### **Advantages:**

Noelle 808-72 mixed system features a medium mixed viscosity for ease of use in specific applications, also features excellent air release properties. This mixed system does not harden appreciably with age as does many other commercially available materials of this type. Noelle 808-72 offers excellent adhesion to a wide variety of substrates and has a fast working life along with good electrical properties.

#### **Physical Properties:**

	<b><u>Resin</u></b>	<b><u>Hardener</u></b>
	808-72A	808-72B
Color:	Clear	Purple
Mix Ratio		
(By Volume)	1.0	1.0
(By Weight)	100.0	100.0

#### **Shelf Life:** (Sealed containers)

Three months @ 25°C (both A+B) Hand agitation of the Resin component is recommended after long standing to insure best results.

#### **Instructions:**

Combine the Resin and the Hardener in the ratio listed above. Mix by hand or mechanical mixer until material is uniform in appearance.

#### **Cure Schedules:**

Cure Temp:  
 25°C 43°C(110°F) 66°C(150°F) 93°C(200°F)  
 (↑ room temp.)  
 Cure Time:  
 1 days 4 hours 2 hours 30 minutes

#### **Cured Properties:**

Shore Hardness, measured @ 25°C >20A  
 Volume Resistivity, Ohm/cm @ 25°C: 7 x 10<sup>15</sup>  
 Dielectric Constant @ 1 MHz @ 25°C: 2.85  
 Dielectric Strength, volts/mil 390  
 Dissipation Factor @ 1 MHz @ 25°C: 0.002  
 Operating Temperature Range: -45°C to +150°C

#### **Storage and Handling:**

Normal storage and handling is at room temperature. Use standard mixing and house keeping procedures to minimize the risk of spills and contact with the surrounding materials.

**All values reported above are typical values, and are reported as a means of reference. Individual testing should be done to determine actual results, tested at specific conditions.**