



Noelle Industries, Inc.
Adhesives • Coatings • Conductives • Encapsulants

NOELLE 809-76 System

A Two Component Tooling Compound

Description:

Noelle 809-76 System is a gray two component (A + B) high performance, room temperature curing, tooling compound. A higher heat dissipating version of Noelle 809-74 System

Advantages:

Noelle 809-76 will cure at temperatures above 15°C (60°F) in a moderate period of time. Noelle 809-76 is an excellent mold making, metal filled tooling compound.

Physical Properties:

	Resin 809-76A	Hardener 809-76B
Color:	Gray	Clear
Specific Gravity	1.56	0.98
Mix Ratio (By Weight)	100.0	12

Shelf Life: (Sealed containers)

One Year @ 25°C (both A+B). Hand agitation of the Resin component is recommended after long standing to insure best results.

Instructions:

Combine the Resin and the Hardener in the ratio listed above. Mix by hand or mechanical mixer until material is uniform in appearance.

Cure Schedules:

16 hours @ 25°C (77°F) will yield 80% of the systems full potential. An additional 48 hours @ 25°C (77°F) will yield the systems full potential.

	80%	100%
Cure Temp:	25°C	25°C
Cure Time:	16 hrs	66 hrs

Pot Life (100 grams) @ 25°C = 60 min

Cured Properties:

Shore Hardness, measured @ 25°C 84D
Operating Temperature Range: -20°C to +100°C

Storage and Handling:

Normal storage and handling is at room temperature. Use standard mixing and housekeeping procedures to minimize the risk of spills and contact with the surrounding materials.

All values reported above are typical values, and are reported as a means of reference. Individual testing should be done to determine actual results, tested at specific conditions.

• 76 Treble Cove Road, Building # 3, Unit C, North Billerica, MA 01862

• Phone: (978) 439-9841 • Fax: (978) 439-9842 • Website: www.noelleindustries.com • email: info@noelleindustries.com